

What is claimed is:

Sub 132
1. A non-aqueous electrolyte secondary battery comprising;
a positive electrode and a negative electrode capable of
intercalating and de-intercalating lithium;
a non-aqueous electrolyte solution; and
a solid electrolyte,

wherein said negative electrode contains a composite particle
constructed such that at least part of a surface of a nuclear particle containing
at least one of tin, silicon and zinc as a constituent element is coated with one
of;

a solid solution, and
an inter-metallic compound,

which are composed of an element included in said nuclear
particle and at least one element, exclusive of the element included in said
nuclear particle, selected from a group of elements in a Periodic Table,
comprising group 2 elements, transition elements, group 12 elements, group
13 elements and group 14 elements exclusive of carbon,

and said solid electrolyte is a polymer gel electrolyte.

2. The non-aqueous electrolyte secondary battery of claim 1,
wherein said positive electrode includes a lithium-containing composite oxide
and a polymer composing said polymer gel electrolyte, and said negative
electrode includes said composite particle and a polymer composing said
polymer gel electrolyte.

3. The non-aqueous electrolyte secondary battery of one of claim 1
and claim 2 wherein main structure of said polymer is one of polyalkylene
oxide and a derivative of the same.

Sub 132
4. The non-aqueous electrolyte secondary battery of one of claim 1

5. The non-aqueous electrolyte secondary battery of one of claim 1 and claim 2, wherein said polymer is a polyester polymer whose main structure is one of polyester and a derivative of the same.

6. The non-aqueous electrolyte secondary battery of one of claim 1 and claim 2, wherein said polymer is a copolymer of methacrylate and an ethylene oxide.

7. The non-aqueous electrolyte secondary battery of one of claim 1 and claim 2, wherein said polymer gel electrolyte includes at least one of structural reinforcements selected from a hydrophobic treated particulate, and a fiber or a non-woven fabric of a polyolefin polymers.

8. A non-aqueous electrolyte secondary battery comprising;
a positive electrode and a negative electrode capable of
intercalating and de-intercalating lithium;
a non-aqueous electrolyte solution; and
a solid electrolyte,

wherein said negative electrode contains a composite particle constructed such that at least part of a surface of a nuclear particle containing at least one of tin, silicon and zinc as a constituent element is coated with one of;

a solid solution, and
an inter-metallic compound,
which are composed of elements included in said nuclear
particle and at least one element, exclusive of the element included in said

Sub 1331 cont
nuclear particle, selected from a group of elements in a Periodic Table, comprising group 2 elements, transition elements, group 12 elements, group 13 elements and group 14 elements exclusive of carbon, and said solid electrolyte is a lithium ion conductive glass-type solid electrolyte.

9. The non-aqueous electrolyte secondary battery of claim 8, wherein said lithium ion conductive glass-type solid electrolyte is synthesized with raw materials including;

a first component including at least a lithium sulfide;

a second component including at least one of a silicon sulfide, a phosphor sulfide and a boron sulfide; and

a third component including at least one of lithium phosphate, lithium sulfate, lithium borate, lithium silicate.

add c/o